

Harpon 321

Chemical Product	CAS #	Breakthrough time (minutes)	Permeation level	Standard	Degradation level	Rating
Ethyl acetate 99%	141-78-6	6	0	EN 16523-1:2015	NT	NA
Formaldehyde 37%	50-00-0	>480	6	EN 16523-1:2015	4	++
Hydrogen peroxide 30%	7722-84-1	>480	6	EN 16523-1:2015	4	++
Methanol 99%	67-56-1	35	2	EN 374-3:2003	NT	NA
Methyl Ethyl Ketone (2-Butanone) 99%	78-93-3	19	1	EN 374-3:2003	NT	NA
Phenol 80%	108-95-2	88	3	EN 16523-1:2015	NT	NA
Sodium hydroxide 40%	1310-73-2	>480	6	EN 16523-1:2015	4	++
Styrene 99%	100-42-5	10	0	EN 16523-1:2015	NT	NA

*not normalized result

OVERALL CHEMICAL PROTECTION RATING

Protection rating is determined by taking into account the effects of both permeation and degradation in an attempt to provide users with an overall protection guideline when using our glove products against specific chemicals.

 Used for **high chemical exposure** or chemical immersion, limited to breakthrough time based on a working day.

 Used for **repeated chemical contact**, limited to total chemical exposure i.e. : accumulative breakthrough time based on a working day.

 **Splash protection only**, on chemical exposure the gloves should be discarded and new gloves worn as soon as possible.

 **Not recommended**, these gloves are deemed unsuitable for work with this chemical.

 NT: Not tested

 NA: "Not applicable" because not fully tested (only degradation OR permeation results)

The chemical test data and overall chemical protection rating should not be used as the absolute basis for glove selection. Actual in-use conditions may vary glove performance from the controlled conditions of laboratory tests. Factors other than chemical contact time